



ESL ELECTROSCIENCE

CERAMIC TAPES &
THICK-FILM MATERIALS

416 EAST CHURCH ROAD
KING OF PRUSSIA, PA 19406-2625 USA

T: 610.272.8000
F: 610.272.6759

www.electroscience.com

MAGNETIC TAPE

40011

Lo-Fire Tape for Multilayer and High Frequency Applications Requiring High Permeability

ESL 40011 is a flexible cast film of magnetic powder dispersed in an organic matrix. It is designed to be fired at 885°C to give a dense body. Multilayer parts can be formed by laminating metallized sheets of the tape into a monolithic structure prior to firing. A pressure/temperature combination of 10.5 MPa and 70°C works well for laminating this tape. Magnetic tape is provided on a silicone-coated polyester film to minimize environmental contamination, to protect it from mechanical damage, and to aid in handling. This material is useful in high frequency applications that require high permeability.

PROCESSING PARAMETERS

LAMINATING:	10.3 MPa (1500 psi) at 70°C
FIRING TEMPERATURE:	900±15°C
TIME AT PEAK TEMPERATURE:	2 – 3 hours

TAPE CHARACTERISTICS

TAPE THICKNESS:	65-75 µm (2.6 – 3.0 mils)
COLOR:	brown
SHELF LIFE:	12 months

40011 0611 Rev C

ESL Affiliates

ESL China • Rm#1707, Tower A • City Center of Shanghai • 100 Zunyi Road • Shanghai, China 200051 Tel: (011-86)-21-62370336 • Fax: (011-86)-21-62370338 • eslchina@eslshanghai.net

ESL Europe • 8 Commercial Road • Reading, Berkshire, England RG2 0QZ • Tel: (011-44)-118-918-2400 • Fax: (011-44)-118-986-7331 • [Sales@ESLEurope.co.uk](mailto:sales@ESLEurope.co.uk)

ESL Nippon • Sukegawa Bldg • 6th floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: (011-81)-3-3864-8521 • Fax: (011-81)-3-3864-9270 • [Sales@ESL-Nippon.co.jp](mailto:sales@ESL-Nippon.co.jp)

See Caution and Disclaimer on other side.

FIRED TAPE PROPERTIES (Using co-fired ESL 903-A silver conductor)

PERMEABILITY:

(100 KHz) ≥ 200

INSULATION RESISTANCE:

(100 VDC) $\geq 10^8 \Omega$

Thermal Coefficient of Expansion:

(25°C to 300°C) 9.4 ppm/°C

BREAKDOWN VOLTAGE:

> 1000 VDC/25 µm

FIRED SHRINKAGE:

(Using recommended processing parameters) X and Y 18 ± 1 %
Z 18 ± 1 %

FIRED DENSITY:

(Theoretical) 5.30 g/cm³

COMPATIBLE CONDUCTORS:

ESL 903-A, 903-B, 902

40011 0611 Rev C

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapors emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. Electro-Science assumes no liability for any injury, loss, or damage, direct or consequential arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make their own tests to determine the suitability thereof for their particular use, before using it. User assumes all risk and liability whatsoever in connection with their intended use. Electro-Science's only obligation shall be to replace such quantity of the product proved defective.
