



Electro-Science Laboratories, Inc.

416 East Church Road • King of Prussia, PA 19406-2625, U.S.A
610-272-8000 • Fax: 610-272-6759 • www.ElectroScience.com • Sales@ElectroScience.com

DIELECTRIC COMPOSITION

4022-F

Low Temperature Firing Sealing Glass for Soda-Lime Glass

ESL 4022-F is a glass paste in screen-printable form, for use in sealing together soda-lime glass plates. It is designed to be processed at low temperatures. Other glass substrates or ceramics having a thermal coefficient of expansion similar to soda-lime glass may also be bonded. ESL 4022-F has a fine particle size distribution and is useful for making thin seal cross-sections. When properly fired, 4022-F produces fairly clear transparent seals for use in a variety of packaging and hermetic seal applications.

PASTE DATA

RHEOLOGY:	Thixotropic, screen printable paste
VISCOSITY: (Brookfield RVT, ABZ Spindle, 10 rpm, 25.5°C ± 0.5°C)	125 ± 25 Pa·s
COLOR:	Transparent Gray
SHELF LIFE:	Six months

PROCESSING

SCREEN MESH/EMULSION	200-325/38 μm
LEVELING TIME:	5-10 minutes
DRYING AT 125° C:	10-15 minutes
FIRING TEMPERATURE:	500°C
RATE OF ASCENT/DESCENT:	20°C-40°C/minute
SUBSTRATE FOR CALIBRATION:	soda-lime glass
THINNER:	ESL 401

4022-F 0304-A

ESL Affiliates

Japan: ESL-Nippon Company, Ltd. • Sukegawa Bldg • 6th floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: (011-81)-3-3864-8521 • Fax: (011-81)-3-3864-9270
NipponSales@ESLNippon.com

China: Shanghai Agmet Electro-Science Laboratory Ltd. • Rm#1707, Tower A • City Center of Shanghai • 100 Zunyi Road • Shanghai, China 200051
Tel: (011-86)-21-62370336 • Fax: (011-86)-21-62370338 • eslchina@guomai.sh.cn

Europe: Agmet, Ltd. • 8 Commercial Road • Reading, Berkshire, England RG2 0QZ • Tel: (011-44)-118-918-2400 • Fax: (011-44)-118-986-7331 • Sales@ESLEurope.co.uk


See Caution and Disclaimer on other side.

TYPICAL PROPERTIES


FIRED THICKNESS:

18 ± 8 μm

Typical Burnoff And Sintering Cycle



Typical Sealing Cycle



4022-F 0304-A

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapors emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. Electro-Science assumes no liability for any injury, loss, or damage, direct or consequential arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make their own tests to determine the suitability thereof for their particular use, before using it. User assumes all risk and liability whatsoever in connection with their intended use. Electro-Science's only obligation shall be to replace such quantity of the product proved defective.