



ESL Electro-Science

416 East Church Road • King of Prussia, PA 19406-2625, U.S.A
610-272-8000 • Fax: 610-272-6759 • www.ElectroScience.com • Sales@ElectroScience.com

SILVER PLATINUM CONDUCTOR

9512-G

Cadmium-Free, Lead-Free and Nickel-Free

ESL 9512-G is a newly developed silver/platinum conductor, which can also be used as an interconnect paste in SOFC and other fuel cells. It exhibits excellent conductivity, adhesion to 96% alumina and tape-cast materials, and solder leach resistance. It is compatible with 4920 dielectric and tape-cast materials that are similarly free of alkali ions and the above metals.

PASTE DATA

RHEOLOGY:	Thixotropic, screen-printable paste
VISCOSITY: (Brookfield RVT, ABZ Spindle, 10 rpm, 25.5°C±0.5°C)	250±25 Pa·s
BONDING MECHANISM:	Mixed
SHELF LIFE: (25°C)	6 months

PROCESSING

SCREEN MESH/EMULSION:	325/25 µm
LEVELING TIME: (25°C)	5-10 minutes
DRYING AT 125°C:	10-15 minutes
FIRING TEMPERATURE:	850°C
TIME AT PEAK:	10-12 minutes
RATE OF ASCENT/DESCENT:	60°C-100°C/minute
TOTAL CYCLE:	50 minutes
SUBSTRATE OF CALIBRATION:	96% alumina
THINNER:	ESL 401

9512-G 0403-A

ESL Affiliates

ESL China • Rm#1707, Tower A • City Center of Shanghai • 100 Zunyi Road • Shanghai, China 200051 Tel: (011-86)-21-62370336 • Fax: (011-86)-21-62370338 • eslchina@guomai.sh.cn

ESL Europe • 8 Commercial Road • Reading, Berkshire, England RG2 0QZ • Tel: (011-44)-118-918-2400 • Fax: (011-44)-118-986-7331 • Sales@ESLEurope.co.uk

ESL Nippon • Sukegawa Bldg • 6th floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: (011-81)-3-3864-8521 • Fax: (011-81)-3-3864-9270 • NipponSales@ESLNippon.com

See Caution and Disclaimer on other side

TYPICAL PROPERTIES

FIRED THICKNESS:	10-15 μm
RESISTIVITY: (at 12.5 μm fired thickness)	$\leq 4 \text{ m}\Omega/\text{sq.}$
PRINTING RESOLUTION: (Line/Space)	75 μm x 75 μm
SOLDER WETTABILITY: (RMA Flux, 5 sec. dip, 62 Sn/36 Pb/2 Ag, 220°C \pm 5°C)	> 95% coverage
SOLDER LEACH: (No. of 10 sec. dips to double resistance of 0.25 mm wide x 100 mm long conductor)	
62 Sn/36 Pb/2 Ag, 220°C \pm 5°C	10 dips
ADHESION: (90° pull, 2.0 mm x 2.0 mm pads, 62 Sn/36 Pb/2 Ag, 220°C \pm 5°C)	
Initial pull strength:	> 70 N
Aged 200 hours at 150°C:	> 70 N

9512-G 0403-A

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapors emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. ESL Electro-Science assumes no liability for any injury, loss, or damage, direct or consequential arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make their own tests to determine the suitability thereof for their particular use, before using it. User assumes all risk and liability whatsoever in connection with their intended use. ESL Electro-Science's only obligation shall be to replace such quantity of the product proved defective.